



# ALL STAINLESS LIMITED

21 Camford Way  
Sundon Park  
Luton, Beds  
LU3 3AN

Telephone: 01582 584075

Facsimile: 01582 585234

E-mail: info@allstainlessltd.co.uk

## INFORMATION SHEET

## STAINLESS STEEL TYPE 304

### TYPE 304 STAINLESS STEEL

This is the most versatile and one of the most widely applied of the 300 series Stainless Steels. It has excellent forming and welding characteristics. The carefully controlled analysis of Type 304 enables it to be deep drawn more severely than Types 301 and 302 without immediate heat softening, a characteristic that has made this grade dominant in the manufacture of drawn stainless parts such as sinks and saucepans. It is readily brake or roll formed into a variety of other parts for application in the industrial, architectural and transportation fields.

Type 304 also has outstanding welding characteristics. Post-weld annealing is not required to restore the excellent performance of this grade in a wide range of mildly corrosive conditions.

Type 304L does not require post-weld annealing and finds extensive use in heavy gauge components where freedom from carbide weld precipitation is often required.

### Corrosion Resistance:

Excellent. Exceeding that of Type 302 in a wide variety of corrosive media including hot petroleum products, steam combustion gases.

### Heat Resistance:

Good oxidation resistance in intermittent service to 1600°F and in continuous service to 1700°F. Continuous use of 304 in 800 – 1575°F range not recommended but often performs well in temperatures fluctuating above and below this range. Type 304L is more resistant to carbide precipitation and can be used in the above temperature range.

### Heat Treatment:

Annealing – heat to 1850-2050°F and cool rapidly. These grades cannot be hardened by thermal treatment.

### Welding:

Excellent. All standard methods. Use type 308 rods or electrodes. Heavy welded sections in Type 304 may require post-weld annealing for maximum corrosion. This is not required if Type 304L is used.

**TYPICAL APPLICATIONS:** The list of applications for this general-purpose grade is very extensive and includes:

Beer Barrels                      Bulk Milk Coolers                      Fire Extinguisher Parts                      Heat exchangers  
Chemical Containers              Wine Storage Tanks                      Food Processing Equipment

	C	Mn	P	S	Si	Cr	Ni
A.I.S.I. ANALYSIS	304 - .08 Max 304L - .03 Max	2.0 Max	.045 Max	.030 Max	1.0 Max	18.0 to 20.0	8.0 to 10.5

TYPICAL MECHANICAL PROPERTIES - ANNEALED	Yield Strength .2% Offset psi	Ultimate Strength psi	Elongation % in 2"	Hardness		Impact Izod Ft. - lbs	Modulus of Elasticity in Tension - psi
				Rb	BHN		
	35,000	84,000	55	80	149	110	28.0 x 10 <sup>6</sup>

OTHER PROPERTIES	Creep Strength 1% Flow in 10,000 hrs at 1000° F psi	Magnetic Permeability at 200 H-annealed	Electrical Resistivity – Microhm – CM at 68°F	Coefficient of Thermal Expansion (In/In/°F x 10 ) 32°F - 212°F	Thermal Conductivity BTU/Ft. <sup>2</sup> /Hr/°F/Ft	
					At 212°F	At 932°F
	17,300	1.02	72	9.6	9.4	12.4

*NOTE: The above information is published as a general guide only and mechanical and physical properties should only be applied from mill certificates issued.*